

Conveyant	Hose			End Fittings		
	1	2	3	CS	SS	BS
Acetaldehyde	C	C	D	X	.	.
Acetic acid (<60%)	A	A	D	X	.	.
Acetic acid (Glacial)	B	B	D	X	.	.
Acetic anhydride	B	B	D	X	.	.
Acetoacetic ester	C	C	D	.	.	.
Acetone	A	A	A	.	.	.
Acetone cyanohydrin	B	B	D	.	.	X
Acetonitrile	B	B	B	.	.	.
Acetophenone	B	B	B	.	.	.
Acetylcetone	B	B	B	.	.	.
Acetyl chloride		PTFE			PTFE	
Acetylene						
Acetylene dichloride	B	B	B	.	.	.
Acetylene tetrachloride	C	C	C	.	.	.
Acrolein (acrylaldehyde)	B	B	B	.	.	.
Acrylic acid	B	B	D	X	.	.
Acrylonitrile	A	A	D	.	.	.
Adipic acid aqueous	A	A	A	X	.	.
Adiponitrile	B	B	B	.	.	.
Allyl alcohol	A	A	A	.	.	.
Allyl bromide	C	C	C	.	.	X
Allyl chloride	C	C	C	.	.	X
Alums aqueous (Saturated)	A	A	A	.	.	.
Aluminium salts excluding halides (Saturated)	A	B	D	.	.	X
Aluminium chloride (Saturated)	A	D	D			Polypropylene
Aminoethyl ethanolamine	B	B	D	.	.	.
Ammonia solution	A	A	D	.	.	X
Ammonia nitrate		PTFE		X	.	X
Aluminium salts excluding halides (Saturated)	A	B	D	.	.	X
Aluminium chloride (Saturated)	A	C	D	.	.	X
Amyl acetate	C	C	C	.	.	.
Amyl alcohol	B	B	B	.	.	.
Amyl chloride	C	C	C	.	.	.
Aniline (dedicated hose)	C	B	X	.	.	X
Animal oils	A	A	A	.	.	.
Anisole	C	C	C	X	.	X
Antimony chloride	B	D	D	X	.	X
Aqua regia	C	D	D			Polypropylene
Aviation fuel	C	C	C	.	.	.
Barium salts (Saturated)	A	B	D	.	.	X
Beer	A	A	D	.	.	.
Benzaldehyde	C	C	D	X	.	X
Benzene	C	C	D	.	.	.
Benzene sulphonic acid	C	C	D	X	.	X
Benzoic acid	A	A	D	.	.	X
Benzoyl chloride	C	C	C	.	.	.
Benzyl alcohol	A	A	A	.	.	.
Benzyl butyl phthalate	B	B	B	.	.	.
Benzyl chloride	C	C	C	X	.	.
Bleach (<12.5% Cl)	C	C	D	.	.	X
Borax aqueous	A	A	A	.	.	X
Boric acid aqueous	A	A	D	X	.	.
Brine (Saturated)	A	C	D	X	.	X

Conveyant	Hose			End Fittir	
	1	2	3	CS	SS
Bromine water (Saturated)					
Butadiene					
Butane liquid					
Butanediol	B	B	B	.	.
Butyl alcohol	A	A	A	.	.
Butyl acetate	C	C	C	.	.
Butyl acrylate	B	B	B	.	.
N. Butylamine	B	B	D	.	.
Butyl benzene	B	B	B	.	.
Butyl benzyl phthalate	B	B	B	.	.
Butyl bromide					
Butyl butyrate	B	B	B	.	.
Butyl carbitol	A	A	A	.	.
Butyl carbitol acetate	C	C	C	.	.
Butyl cellosolve	A	A	A	.	.
Butyl cellosolve acetate	C	C	C	.	.
Butylene glycol	A	A	A	.	.
Butyl ether	B	B	B	.	.
Butyl ethyl ether	B	B	B	.	.
Butyl methacrylate	C	C	C	.	.
Butyl methoxyethyl ether	C	C	C	.	.
Butyl phthalate	A	A	A	.	.
Butyl stearate	B	B	B	.	.
Butyraldehyde	C	C	D	.	.
Butyric acid (<20%)	B	B	B	.	.
Butyrolactone	C	C	C	.	.
Calcium salts excluding halides and hypochlorite (Saturated)	A	B	D	.	.
Calcium alkyl salicylate solution	A	A	D	.	.
Calcium chloride (Saturated)	A	C	D	X	.
Calcium hypochloride (<12.5% Cl)	C	C	D	X	.
Camphor oil	C	C	C	.	.
Caprylic acid	A	A	A	.	.
Carbinols	B	B	B	.	.
Carbitols	B	B	B	.	.
Carbitol acetate	C	C	C	.	.
Carbolic acid	A	A	D	.	.
Carbolic oil (middle oil)	C	C	C	.	.
Carbon disulphide	C	C	C	.	.
Carbon tetrachloride	C	C	C	.	.
Carbonic acid	A	A	D	.	.
Cashew nut shell oil	B	B	B	.	.
Caustic potash (<50%)	A	B	D	.	.
Caustic soda (<50%)	A	B	C	.	.
Cellosolve	B	B	B	.	.
Chloroacetic acid	B	D	D		
Chlorine					
Chlorobenzene	C	C	C	.	.
Chlorobutane	C	C	C	.	.
Chloroform	C	C	C	.	.
Chloroprene	C	C	C	X	.
Chloropropionic acid	C	C	D	X	.
Chlorosulphonic acid					
Chlorotoluene	C	C	C	.	.