

Conveyant	Hose			End Fittings		
	1	2	3	CS	SS	BS
Fuel oil	B	B	B	.	.	.
Furfural	B	B	B	.	.	.
Furfuryl alcohol	B	B	B	.	.	.
Gallic acid solution	A	A	C	.	.	.
Gasoline	B	B	B	.	.	.
Gelatine aqueous	A	A	A	.	.	.
Gluconic acid	A	A	C	.	.	.
Glucose aqueous	A	A	A	.	.	.
Glycerine	A	A	A	.	.	.
Green sulphate liquor	B	B	D	X	.	X
Glycols aqueous	A	A	A	.	.	.
Glycolic acid aqueous (<37%)	A	A	D	.	.	.
Heptane	B	B	B	.	.	.
Heptanoic acid	B	B	D	X	.	X
Heptanol	A	A	A	.	.	.
Heptanone	B	B	B	.	.	.
Heptene	A	A	A	.	.	.
Hexamethylene diamine	B	B	C	.	.	.
Hexene	B	B	B	.	.	.
Hexanol	A	A	A	.	.	.
Hexylamine	B	B	D	.	.	.
Hexane	A	A	A	.	.	.
Hexylene glycol	A	A	A	.	.	.
Hydrazine hydrate	B	B	D	X	.	X
Hydrobromic acid (<50%)	A	D	D	Polypropylene or PVDF coated steel		
Hydrochloric acid (<37%)	C	D	D			
Hydrofluoric acid (<50%)	C	D	D			
Hydrofluosilicic acid	A	A	D	X	.	.
Hydrogen peroxide (<50%)	B	B	D	X	.	X
Hydrogen sulphide aqueous (Saturated)	A	D	D	X	.	X
Hexamethylene diamine	B	B	D	.	.	.
Hexamethylene tetramine	B	B	D	.	.	.
Hydroquinone	A	A	A	.	.	X
Iodine solution	B	D	D	.	.	X
Iron salts excluding halides (Saturated)	A	B	D	.	.	.
Iron halides	A	D	D	Polypropylene		
Isoamyl acetate	B	B	B	.	.	.
Isoamyl alcohol	B	B	B	.	.	.
Isoamyl bromide	B	D	D	X	.	X
Isoamyl butyrate	B	B	B	.	.	.
Isoamyl chloride	C	C	D	X	.	X
Isoamyl ether	B	B	B	.	.	.
Isoamyl alcohol	A	A	A	.	.	.
Isoamyl acetate	B	B	B	.	.	.
Isoamyl acrylate	B	B	B	.	.	.
Isobutylamine	B	B	D	.	.	.
Isobutyl bromide	B	D	D	X	.	X
Isobutyl chloride	B	D	D	X	.	X
Isobutyl formate	C	C	C	.	.	.
Isobutyl methyl ketone	B	B	B	.	.	.
Isobutyraldehyde	B	B	D	.	.	.
Isobutyl ether	C	C	C	.	.	.
Isooctane	C	C	C	.	.	.
Isodecyl alcohol	A	A	A	.	.	.
Isopentane	C	C	C	.	.	.
Isopentene	C	C	C	.	.	.
Isophorone	B	B	B	.	.	.
Isoprene	B	B	B	.	.	X
Isopropyl alcohol	A	A	A	.	.	.
Isopropanolamine	B	B	D	.	.	.
Isopropyl acetate	C	C	C	.	.	.
Isopropylamine	B	B	D	.	.	.
Isopropylbenzene	B	B	B	.	.	.
Isopropyl chloride	B	D	D	X	.	X
Isopropyl ether	C	C	C	.	.	.
Isopropyl toluene	B	B	B	.	.	.
Jame	A	A	B	.	.	.
Jet fuel	C	C	C	.	.	.
Kerosene	B	B	B	.	.	.
Ketones	B	B	B	.	.	.
Lactic acid (<20%)	A	B	B	.	.	.
Lanolin	A	A	A	.	.	.
Lard	A	A	A	.	.	.
Latex (Low viscosity)	A	A	A	.	.	.
Lauryl alcohol	B	B	B	.	.	.
Lead alkyls	A	A	A	.	.	X
Lead salts (Saturated)	A	B	D	X	.	X
Ligroin	C	C	C	.	.	.

Conveyant	Hose			End Fittings		
	1	2	3	CS	SS	BS
Limonene	B	B	B	.	.	.
Linseed oil	A	A	A	.	.	.
Lubricating oil	B	B	B	.	.	.
Magnesium salts (Saturated)	A	B	D	X	.	X
Maleic acid in solution	A	B	D	X	.	.
Maleic anhydride in solution	B	B	D	X	.	.
Malic acid in solution	B	B	D	X	.	X
Manganese salts (Saturated)	A	B	D	X	.	X
Mercuric chloride (Saturated)	A	D	D	.	.	.
Mesityl oxide	A	A	B	.	.	.
Methacrylic acid	B	B	D	.	.	.
Methyl alcohol	A	A	A	.	.	.
Methyl acetate	C	C	C	.	.	.
Methyl aceto acetate	C	C	D	X	.	.
Methyl acetone	B	B	B	.	.	.
Methyl acrylate	B	B	B	.	.	.
Methylamine	B	B	C	.	.	.
Methylamyl acetate	C	C	C	.	.	.
Methylamyl alcohol	B	B	B	.	.	.
Methyl amyloketone	B	B	B	.	.	.
Methyl tert-butyl ether	C	C	C	.	.	.
Methyl butyl ketone	B	B	B	.	.	.
Methyl cellosolve	B	B	B	.	.	.
Methyl cellosolve acetate	C	C	C	.	.	.
Methyl chloride	A	A	A	X	.	.
Methyl cyanide	B	B	B	.	.	.
Methyl cyclohexane	B	B	B	.	.	.
2-methyl pentene	C	C	C	.	.	.
Methylene bromide	C	C	D	.	.	.
Methylene chloride	C	C	C	.	.	.
Methyl ethyl ketone	C	C	C	.	.	.
Methyl ethylpyridine	C	C	C	.	.	X
Methyl formate	C	C	C	.	.	.
Methyl isobutyl ketone	C	C	C	.	.	.
Methyl methacrylate	C	C	C	.	.	.
Methyl nitrobenzene	B	B	B	.	.	.
Methyl pentene	B	B	B	.	.	.
Methyl pyridine	B	B	B	.	.	.
Methylstyrene	B	B	B	.	.	.
Mineral jelly	A	A	A	.	.	.
Mineral oil	B	B	B	.	.	.
Mineral spirits	B	B	B	.	.	.
Mineral wax	D	D	D	.	.	.
Molasses	A	A	A	.	.	.
Monoethanolamine	A	A	B	.	.	.
Monoethylamine	B	B	C	.	.	.
Monoisopropanolamine	B	B	D	.	.	.
Mononitrobenzene	B	B	B	.	.	.
Morpholine	B	B	C	.	.	.
Motor fuel anti-knock compounds (leaded)		PTFE		.	.	X
Motor fuel anti-knock compounds (unleaded)	B	B	B	.	.	.
Naphtha	B	B	B	.	.	.
Naphtha solvent	C	C	C	.	.	.
Naphthalene (in solution)	A	A	A	.	.	.
Naphthalene molten	D	D	D	X	X	X
Neohexane	B	B	B	.	.	.
Nickel chloride (Saturated)	A	D	D	X	.	X
Nickel salts, excluding chloride (Saturated)	A	B	D	X	.	X
Nitric acid (<10%)	A	A	D	X	.	X
Nitric acid (10-60%)	C	C	D	X	.	X
Nitric acid (>60%)						
Nitrobenzene	B	B	B	.	.	X
O-nitrophenol (soln)	A	A	D	.	.	.
Nitropropane	B	B	B	.	.	.
Nitrotoluene	B	B	B	.	.	.
Nonane	B	B	B	.	.	.
Nonyl alcohol	B	B	B	.	.	.
Nonylphenol	B	B	C	.	.	.
Octane	B	B	B	.	.	.
Octanol	B	B	B	.	.	.
Octyl acetate	C	C	C	.	.	.
Octyl acrylate	B	B	B	.	.	.
Oils most commercial	B	B	B	.	.	.
Oleic acid	B	B	D	X	.	X
Oleum		PTFE		X	.	X
Oxalic acid (<50%)	B	B	D	X	.	X